

X 210Cr 12

1.2080

BD3

D3

Richtanalyse / chemical analysis in %

C	Si	Mn	P	S	Cr	Mo	Ni	V	W
1,90	0,10	0,25			11,00	-	-	-	-
-	-	-	<	<	-				
2,20	0,40	0,45	0,025	0,020	12,00	-	-	-	-


Wärmebehandlung / heattreatment advice

Härteempfehlung
recommendation of hardening

930-970°C / 1710-1775°F

Abschreckmittel
quenching medium

Öl / oil
Luft / air



Anwendungsbeispiele / examples of use

- Hochleistungsindustriemesser / heavy duty industrial knives
- Scherenmesser / shear knives
- Papiermesser / paper knives

und andere Industriemesser / and other industrial knives