

X155 CrVMo 12

1.2379

BD2

D2

Richtanalyse / chemical analysis in %

C	Si	Mn	P	S	Cr	Mo	Ni	V	W
1,50	0,20	0,25			11,00	0,65	-	0,90	-
-	-	-	<	<	-	-		-	
1,60	0,40	0,45	0,025	0,020	12,00	0,85	-	1,10	-


Wärmebehandlung / heattreatment advice

Härteempfehlung
recommendation of hardening

1020-1050°C / 1870-1920°F

Abschreckmittel
quenching medium

Öl / oil
Luft / air



Anwendungsbeispiele / examples of use

- Hochleistungsindustriemesser / heavy duty industrial knives
- Scherenmesser / shear knives
- Papiermesser / paper knives

und andere Industriemesser / and other industrial knives